



Corporate Headquarters

CAB Incorporated
5411 Cole Road Buford, GA USA 30518
800/241-7311 678/745-2100 Fax 678/745-2082
www.cabinc.com email: sales@cabinc.com

Texas Manufacturing Facility

CAB Incorporated
2306 Rayburn Drive, Nacogdoches, TX USA 75961
800/435-2643 936/569-9430 Fax 936/569-0795

Common Forged Material Comparison Chart

Specification		Grade or Class	Chemical Composition, max (unless range is given), %										Tensile Properties, min (unless range is given)					Energy Value, ft.lbf						
			C	Si	Mn	S	P	Cu	Ni	Cr	Mo	V	Cb/Nb	N	Hardness HB, max	Tensile Strength min, ksi	Yield Point ksi	Yield Strength ksi @ 0.2%	Elongation in 2 in, %	Reduction of Area, %	CVN min avg of 3 specimens	CVN min for single specimen	Testing Temp., F	
AISI		1020	0.17-0.23		0.30-0.60	0.050	0.040																	
AISI		1025	0.22-0.28		0.30-0.60	0.050	0.040																	
AISI		1030	0.27-0.34		0.60-0.90	0.050	0.040																	
AISI		1040	0.37-0.44		0.60-0.90	0.050	0.040																	
AISI		1045	0.42-0.50		0.60-0.90	0.050	0.040																	
AISI		4130	0.28-0.33	0.15-0.30	0.40-0.60	0.040	0.035			0.80-1.10	0.15-0.25													
AISI		4140	0.38-0.43	0.15-0.30	0.75-1.00	0.040	0.035			0.80-1.10	0.15-0.25													
AISI		4330	0.28-0.33	0.15-0.30	0.60-0.80	0.040	0.035		1.65-2.00	0.70-0.90	0.20-0.30													
AISI		4340	0.37-0.43	0.15-0.30	0.60-0.80	0.040	0.035		1.65-2.00	0.70-0.90	0.20-0.30													
AISI		8620	0.18-0.23	0.15-0.30	0.70-0.90	0.040	0.035		0.40-0.70	0.40-0.60	0.15-0.25													
AISI		8625	0.23-0.28	0.15-0.30	0.70-0.90	0.040	0.035		0.40-0.70	0.40-0.60	0.15-0.25													
AISI		8630	0.28-0.33	0.15-0.30	0.65-0.95	0.040	0.035		0.35-0.75	0.40-0.60	0.15-0.25													
ASTM A105	Carbon Steel, Piping		0.35	0.10-0.35	0.60-1.05	0.040	0.035	0.40	0.40	0.30	0.12	0.08		187	70	36	22	30						
ASTM A181	Carbon Steel, General	60	0.35	0.10-0.35	1.10	0.050	0.050								60	30	22	35						
ASTM A266	Carbon Steel, Pressure Vessel Components	70	0.35	0.10-0.35	1.10	0.050	0.050								70	36	18	24						
ASTM A350	Carbon and Low Alloy Steel, Piping Components	1	0.30	0.15-0.35	0.40-1.05	0.025	0.025								60-85	30	23	38						
		2	0.30	0.15-0.35	0.40-1.05	0.025	0.025								70-95	36	20	33						
		3	0.35	0.15-0.35	0.80-1.35	0.025	0.025								70-95	36	20	33						
		4	0.30	0.15-0.35	0.80-1.35	0.025	0.025								75-100	37.5	19	30						
		LF1	0.30	0.15-0.35	0.60-1.35	0.040	0.035	0.40	0.40	0.30	0.12	0.08	0.02		60-85	30	25	38	13	10	-20			
ASTM A521	Closed Die Forging, General use	LF2-1	0.30	0.15-0.35	0.60-1.35	0.040	0.035	0.40	0.40	0.30	0.12	0.08	0.02		70-95	36	22	30	15	12	-50			
		LF2-2	0.30	0.15-0.35	0.60-1.35	0.040	0.035	0.40	0.40	0.30	0.12	0.08	0.02		70-95	36	22	30	20	15	0			
		LF3-1	0.20	0.20-0.35	0.90	0.040	0.035	0.40	3.30-3.70	0.30	0.12	0.03	0.02		70-95	37.5	22	35	15	12	-150			
		LF3-2	0.20	0.20-0.35	0.90	0.040	0.035	0.40	3.30-3.70	0.30	0.12	0.03	0.02		70-95	37.5	22	35	20	15	-150			
		LF5-1	0.30	0.20-0.35	0.60-1.35	0.040	0.035	0.40	1.00-2.00	0.30	0.12	0.03	0.02		60-85	30	25	38	15	12	-75			
		LF5-2	0.30	0.20-0.35	0.60-1.35	0.040	0.035	0.40	1.00-2.00	0.30	0.12	0.03	0.02		70-95	37.5	22	35	15	12	-75			
		LF6-1	0.22	0.15-0.30	1.15-1.50	0.025	0.025	0.40	0.40	0.30	0.12	0.04-0.11	0.02	0.01-0.03		66-91	52	22	40	15	12	-60		
		LF6-2	0.22	0.15-0.30	1.15-1.50	0.025	0.025	0.40	0.40	0.30	0.12	0.04-0.11	0.02	0.01-0.03		75-100	60	20	40	20	15	-60		
		LF6-3	0.22	0.15-0.30	1.15-1.50	0.025	0.025	0.40	0.40	0.30	0.12	0.04-0.11	0.02	0.01-0.03		75-100	60	20	40	20	15	0		
		LF9	0.20		0.40-1.06	0.040	0.035	0.75-1.25	1.60-2.24	0.30	0.12	0.03	0.02		63-88	46	25	38	13	10	-20			
		LF787-2	0.07	0.40	0.40-0.70	0.025	0.025	1.00-1.30	0.70-1.00	0.60-0.90	0.15-0.25	0.03	0.02 min		65-85	55	20	45	15	12	-75			
		LF787-3	0.07	0.40	0.40-0.70	0.025	0.025	1.00-1.30	0.70-1.00	0.60-0.90	0.15-0.25	0.03	0.02 min		75-95	65	20	45	15	12	-100			
		AA													80	50	24	40						
		AB													80	55	26	52						
		AC													96	70	20	50						
		AD													90	65	20	50						
		AE													105	80	20	50						
		AF													125	105	16	50						
		AG													145	120	15	45						
		AH													170	140	13	40						
		CA													60	30	25	36						
		CC													66	33	23	36						
		CC1													75	37	24	40						
		CE													80	40	22	36						
		CF													85	44	25	40						
		CG													90	55	20	39						
ASTM A668	Carbon Steel Forging	A (AH)			1.35	0.050	0.050								183	47								
		B (BH)			1.35	0.050	0.050								120-174	60	30	24	36					
		C (CH)			1.35	0.050	0.050								137-183	66	33	22	34					
		D (DH)			1.35	0.050	0.050								149-207	75	37	19	30					
		E (EH)			1.35	0.050	0.050								174-217	83	43	22	35					
		F (FH)			1.35	0.050	0.050								174-217	82	48	48	19	36				
		G (GH)				0.040	0.040								163-207	80	50	22	38					
		H (HH)				0.040	0.040								187-235	90	58	58	18	40				
		J (JH)					0.040	0.040							207-255	90	65	65	18	48				
		K (KH)						0.040	0.040						207-269	100	75	75	18	48				
		L (LH)							0.040	0.040					223-293	110	85	85	14	40				
		M (MH)								0.040	0.040					269-341	135	110	12	38				
		N (NH)									0.040	0.040					321-402	160	130	11	35			